



Product: Marmiro® Bluestone Paver

Type: Sandstone

Origin: Asia

Color: Charcoal grey stone with a wavy texture throughout

Flamed Finished: When an intense flame is fired at the stone, causing the surface to burst and become rough.

[Recommended Installation Guidelines](#)

TECHNICAL SPECIFICATIONS

Compressive Strength ASTM - C170

Sample	Antiqued	Sandblasted
Marmiro® Bluestone Sandstone	N/A	10,325 psi

Flexural Strength ASTM - C880

Sample	Antiqued	Sandblasted
Marmiro® Bluestone Sandstone	N/A	1,200 psi

Freeze and Thaw ASTM - C666

Sample	Results	Notes
Marmiro® Bluestone Sandstone	Pass	No cracks or deformations noted.

Water Absorption ASTM - C97

Sample	Antiqued Water Absorption %	Sandblasted Water Absorption %
Marmiro® Bluestone Sandstone	N/A	0.83%

Density ASTM - C97

Sample	Antiqued Density	Sandblasted Density
Marmiro® Bluestone Sandstone	N/A	168.5 lbs/ft³

DISCLAIMER

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.